

POLES - GENERAL

ALL WOOD POLES ARE TO COMPLY WITH ANSI 05.1 FOR WOOD POLE SPECIFICATIONS AND DIMENSIONS. POLES ARE TO BE STRAIGHT AND NO BENDS.

YELLOW PINE POLES ARE TO BE TREATED WITH PENTACHLOROPHENOL. ANY OTHER TREATMENTS MUST BE APPROVED BY THE ENVIRONMENTAL AND ENGINEERING DEPARTMENTS. ALL POLE TREATMENTS/PRESERVATIVES MUST CONFORM TO AWPA AND EPA STANDARDS.

ALL WOOD POLES WITH PRESERVATIVES OR CHEMICAL TREATMENTS ARE TO BE INSTALLED WITH A PHYSICAL BARRIER BETWEEN THE POLE AND SOIL TO PREVENT POTENTIAL PRESERVATIVE MIGRATION AND DECAY OF POLE. THE BARRIER IS TO EXTEND ABOVE THE GROUND LINE.

BURLINGTON ELECTRIC DEPT.	
DISTRIBUTION STANDARDS	
POLES AND FIXTURES GENERAL	
DATE: 08/07/14	DWG. NO.: 050101
DWN BY: RG	APP. BY:
SCALE: NONE	SHEET 1 OF 1